ATB-AGM-DC12-24

Deep-cycle AGM.
Built for repeated cycling.

A 12 V 24 Ah deep-cycle AGM VRLA battery engineered for repeated discharge to 50% DoD or deeper. A rugged thick-plate grid design and high active-material density give high cycle life in motive power, solar and renewable-energy storage and marine use. Sealed, maintenance-free and non-spillable, with M5 bolt terminals.



12 V	24 Ah	420 A	8.5 kg
NOMINAL VOLTAGE	C20 CAPACITY @ 25°C	MAX DISCHARGE (5 S)	APPROX. WEIGHT

Sealed AGM VRLA
Valve-regulated oxygen-recombination design. Maintenance-free and non-spillable: no electrolyte topping and no acid handling.

M5 bolt terminals
Threaded M5 terminals for secure bolted cable connections in UPS and standby systems.

Deep-cycle design
Thick plates and high active-material density for repeated deep discharge.

Standard footprint
165 × 175 × 127 mm case.

SPECIFICATIONS


MECHANICAL

Length	**165 mm ±1.5**
Width	**175 mm ±1.5**
Container height	**127 mm ±1.5**
Overall height	**127 mm ±1.5**
Approx. weight	**8.5 kg ±5%**
Container material	**ABS, UL94-HB (UL94-V0 optional)**
Terminal type	**M5 bolt terminal**

ELECTRICAL

Nominal voltage	**12 V**
Chemistry	**AGM VRLA (sealed)**
Capacity, 20 hr (C20)	**24 Ah**
Capacity, 10 hr (C10)	**20 Ah**
Capacity, 5 hr (C5)	**18 Ah**
Rating basis	**to 1.75 V/cell @ 25°C**
Float voltage @ 25°C	**13.5 – 13.8 V**
Equalizing voltage @ 25°C	**14.4 – 15.0 V**
Max charge current	**8.4 A**
Max discharge current	**420 A (5 s)**
Internal resistance (charged)	**≈ 9.0 mΩ**
Operating temp. (dis / chg)	**−15°C~50°C / −15°C~40°C**
Storage temp.	**−15°C~40°C**

CONTAINER DRAWING — DIMENSIONS IN MM



ATB-AGM-DC12-24 — technical data

CONSTANT CURRENT DISCHARGE @ 25°C · UNIT: A · ATB DERATED

F.V (V/cell) / Time	5 min	15 min	30 min	1 h	3 h	5 h	10 h	20 h
1.60 V	73.5	35.7	20.8	12.9	5.57	3.75	2.07	1.23
1.67 V	67.5	34.2	20.2	12.6	5.48	3.69	2.04	1.22
1.70 V	64.7	33.6	19.9	12.5	5.42	3.66	2.02	1.22
1.75 V	60.2	32.4	19.4	12.3	5.35	3.60	2.00	1.20
1.80 V	56.0	31.2	19.0	12.1	5.26	3.57	1.98	1.19
1.85 V	51.4	29.9	18.5	11.8	5.20	3.51	1.95	1.17

CONSTANT POWER DISCHARGE @ 25°C · UNIT: W/CELL · ATB DERATED

F.V (V/cell) / Time	5 min	15 min	30 min	1 h	3 h	5 h	10 h	20 h
1.60 V	135	66.9	39.3	24.7	10.9	7.35	4.11	2.48
1.67 V	126	64.4	38.4	24.3	10.7	7.23	4.05	2.44
1.70 V	121	63.2	37.8	24.1	10.6	7.17	4.02	2.43
1.75 V	113	61.4	37.2	23.7	10.4	7.11	3.95	2.40
1.80 V	105	59.6	36.6	23.4	10.4	7.02	3.92	2.37
1.85 V	97.6	57.8	35.7	23.0	10.2	6.93	3.89	2.35

EFFECT OF TEMPERATURE ON CAPACITY (20 HR)

Temperature	Capacity (20 HR)
40 °C	102%
25 °C	100%
0 °C	85%
−15 °C	65%


SELF-DISCHARGE CHARACTERISTICS

Storage time	Remaining capacity
3 months	91%
6 months	82%
12 months	64%

CHARACTERISTIC CURVES


Discharge Characteristics

TERMINAL VOLTAGE (V/CELL) vs DISCHARGE TIME · 25°C / 20°C




Charging Characteristics

0.1 CA · 2.25 V/CELL @ 25°C




Capacity Retention (Self-Discharge)

CAPACITY RETENTION RATIO vs STORAGE TIME



Float Service Life

FLOAT LIFE vs BATTERY TEMPERATURE · 2.25 V/CELL



STANDARDS & QUALITY

AGM VRLA batteries produced by an ATB-approved manufacturing partner whose VRLA batteries are UL-recognized components under UL 1989, in facilities certified to ISO 9001, ISO 14001 and ISO 45001. Sealed, non-spillable VRLA construction.

Values are subject to variation of ±5% under normal manufacturing processes. Technical specifications are subject to change without prior notice. Curves represent typical performance for the AGM VRLA cell platform at the stated reference conditions. This product is engineered, specified and branded by ATB Power. E&OE. © ATB Power.